

Limecoat Line

Limestucco Estructurado

Installation manual · Lime stucco



Technical data sheet, colour chart and the product's remaining documentation:

formmadesign.com/documentacion/limecoat/limestucco

01 — BEFORE YOU START

The substrate must be sound, clean, dry, stable and flat.

Repair cracks, voids, spalling and irregularities beforehand.

02 — PREPARING THE SUBSTRATE

Use Limeprimer where uneven substrates or differences in absorbency need to be evened out.

03 — PREPARING THE PRODUCT

Limestucco Estructurado is supplied ready to use.

Stir to a uniform consistency before applying.

It accepts adjustment with up to 5% water to improve the texture. Do not exceed that proportion: it reduces coverage and the strength of the lime.

04 — APPLICATION

Apply with a trowel or spatula in two thin coats.

Grain size of approximately 700 µm. Application must respect the presence of the aggregate and build a more material surface, avoiding excessive build-up or unnecessary differences in thickness.

Approximate consumption 1 kg/m² per coat · 2 kg/m² total, approximate

05 — DRYING

Between coats 6 h

Full drying time 24 h

Some plasterers apply the second coat while the first is still damp. It is a trade practice that changes the final expression: validate it beforehand with a sample.

06 — APPLICATION CONDITIONS

Ambient temperature 5–30 °C

07 — SHOWERS AND DIRECT WATER CONTACT

In showers only Limestucco Fine is recommended.

Limestucco Textured is not recommended in showers or areas of direct water contact: its coarser texture makes cleaning harder and can lead to poorer ageing.

08 — SHELF LIFE

Storage	Original sealed container
Shelf life	Max. 12 months in a sealed container